



Endex International

Innovation for the Future

ENDEX 100™

Endothermic Chemical Foaming and Nucleating Agent

Endex 100™ is a 100% active, free-flowing powder. It can be used in a wide range of commodity and engineering plastics, combining quality and efficiency with the benefits of versatility and cost effectiveness.

Endex 100™ endothermic chemical foaming agent is also a very effective nucleating agent in physical foaming processes. Its free-flowing properties make it easy to feed using conventional metering equipment. It can also be batch blended with pelletized resin using an adhesion promoter, for example, mineral oil at 1.5 oz per 100 pound (or 45 g per 50 kg) of resin.

Endex 100™ liberates carbon dioxide gas in a controlled manner when subjected to thermoplastic processing temperatures, and decomposes endothermically, absorbing heat from the polymer. This usually results in shorter cycle times in injection molding, or increased extrusion rates.

Endex 100™ use levels will vary with the application, but the following guidelines can be used as a starting point. Optimization for each application is recommended:

- Structural foam molding 0.50%
- Nitrogen foam molding 0.15 - 0.25 %
- Sink mark elimination 0.10%
- Extrusion, blow molding 0.20 - 0.50 %
- Rotational molding 0.50%
- Nucleation 0.30 - 0.50 %

Endex 100™ has many advantages for the plastics processor, including:

- Fine cell structure
- Shorter cycle times
- Faster extrusion
- Thick, smooth skins in SFM
- Fast degassing
- Fast painting and decorating
- No plate-out on molds
- Beryllium-copper compatible
- G.R.A.S. or FDA sanctioned ingredients.

Endex 100™ is available in 1000 lb boxes.

Contacting Endex International

Canada:

487 Westney Road South, Unit #8
Ajax, Ontario L1S 6W8
Phone: 905.686.4335
Fax: 905.686.6691

USA:

111 Main Street, Box 381
Kingston, Illinois, USA
60145
Phone: 815.784.2446
Fax: 815.784.6012

UK:

9 Abbey Close
Alcester, B49 5QW
Phone: 01 789 765762
Fax: 01 789 765572

You can also visit our website at: www.endexint.net or email us at info@endexint.net for more information.

Note: To the best of our knowledge, the above information is correct. Since the way these products may be used is beyond our control, no responsibility is accepted by Endex International, Inc. for any loss or expense arising from their use. No liability is accepted if use of these products infringes any patent.